

# Resistance and compatibility of OTTOSEAL® S 67 with disinfectants

OTTOSEAL® S 67 with disinfectants					
Trade name	Manufacturer	Conc.	Active substances	Resistance	Compatibility
Buraton 3025	Schülke	3 %	Glutaral	+	Discolouration possible
Incidin Rapid	Ecolab	3 %	Glutaral, benzalkonium chloride, didecyldimethylammonium chloride	+	Discolouration possible
Room Care R 2	Diversey	3 %	Alkyldimethylbenzylammonium chloride	+	+
Room Care R 7	Diversey	3 %	Dodecylbenzenesulphonate	+	+
Torvan concentrate	Kiehl	3 %	Polyalkylene glycol ether	+	+
Surfa Safe	Anios	3 %	Didecyldimethylammonium chloride, polyhexamethylbiguanide	+	+
		100 %	Isopropyl	+	+
		100 %	Ethylalcohol	+	+
		10 %	Hydrogen peroxide	+	+
		30 %	Hydrogen peroxide	+	+
		12 %	Sodium hypochlorite	+	+

+ = resistant

O = temporarily resistant

- = not resistant

The tests were carried out at room temperature.

Please note technical data sheet!